

金属材料記号対象表 - 炭素鋼

単位 μm

日本	ドイツ		イギリス		フランス	イタリア	スペイン	スウェーデン	アメリカ	中国
	JIS	W.-nr.	DIN	BS	EN	AFNPR	UNI	UNE	SS	AISI/SAE
STKM 12A	1.0038	RSt.37-2	4360 40 C	-	E 24-2 Ne	-	-	1311	A570.36	15
STKM 12C										
-	1.0401	C15	080M15	-	CC12	C15, C16	F.111	1350	1015	15
-	1.0402	C22	050A20	2C	CC20	C20, C21	F.112	1450	1020	20
SUM22	1.0715	9SMn28	230M07	1A	S250	CF9SMn28	F.2111	1912	1213	Y15
							11SMn28			
SUM22L	1.0718	9SMnPb28	-	-	S250Pb	CF9SMnPb28	11SMnPb28	1914	12L13	-
-	1.0722	10SPb20	-	-	10PbF2	CF10Pb20	10SPb20	-	-	-
-	1.0736	9SMn36	240M07	1B	S300	CF9SMn36	12SMn35	-	1215	Y13
-	1.0737	9SMnPb36	-	-	S300Pb	CF9SMnPb36	12SMnP35	1926	12L14	-
S15C	1.1141	Ck15	080M15	32C	XC12	C16	C15K	1370	1015	15
S25C	1.1158	Ck25	-	-	-	-	-	-	1025	25
-	1.89	StE380	4360 55 E	-	-	FeE390KG	-	2145	A572-60	-
-	1.0501	C35	060A35	-	CC35	C35	F.113	1550	1035	35
-	1.0503	C45	080M46	-	CC45	C45	F.114	1650	1045	45
-	1.0726	35S20	212M36	8M	35MF4	-	F210G	1957	1140	-
-	1.1157	40Mn4	150M36	15	35M5	-	-	-	1039	40Mn
SMn438(H)	1.1167	36Mn5	-	-	40M5	-	36Mn5	2120	1335	35Mn2
SCMn1	1.117	28Mn6	150M28	14A	20M5	C28Mn	-	-	1330	30Mn
S35C	1.1183	Cf35	060A35	-	XC38TS	C36	-	1572	1035	35Mn
S45C	1.1191	Ck45	080M46	-	XC42	C45	C45K	1672	1045	Ck45
S50C	1.1213	Cf53	060A52	-	XC48TS	C53	-	1674	1050	50
-	1.0535	C55	070M55	9	-	C55	-	1655	1055	55
-	1.0601	C60	080A62	43D	CC55	C60	-	-	1060	60
S55C	1.1203	Ck55	070M55	-	XC55	C50	C55K	-	1055	55
S58C	1.1221	Ck60	080A62	43D	XC60	C60	-	1678	1060	60Mn
-	1.1274	Ck101	060A96	-	XC100	-	F.5117	1870	1095	-
SK3	1.1545	C105W1	BW1A	-	Y105	C36KU	F.5118	1880	W1	-
SUP4	1.1545	C105W1	BW2	-	Y120	C120KU	F.515	2900	W210	-